



ALPHA STONE

For grinding & packing
Calcium carbonate



AS-352

Typical Chemical Properties

CaCO ₃	99.8
CaO	55.6
MgO	0.15
Fe ₂ O ₃	0.003
Al ₂ O ₃	0.002
SiO ₂	0.01 – 0.03
L.OI	44.02

Typical Physical Properties

Brightness (Ry) %	95
Whiteness (L*) %	98
Refractive index %	1.59
pH Value (787/9)	9 Max
Loose bulk density (gm/cm ³)	1.4±0.2
Hardness (Mohs*)	3
Moisture %	0.25 Max

PSD

Over 2 mm	≤ 1 %
between 500 μ and 1.7 μ	≈ 85 %
Under 106 μ	≤ 8 %

Factory: Egypt- El Minya- industrial zone –El-Motahra

HQ Office :66 Mohamed Farid Abo Haded St., Nasr city , Cairo

Tel: (+2) 0862290004 – 0869202737 - 022876613

Fax: (+2) 0862290005 - 022876613

Mobile : (+2) 01001050113 -01227348893- 01003405080

المصنع : مصر- محافظة المنيا –المنطقة الصناعية –المطاهرة

المقر الإداري: 66 شارع محمد فريد أبو حديد - القاهرة - مدينة نصر

ت: (+2) 0862290004 – 0869202737 – 022876613

فاكس: (+2) 0862290005 - 022876613

موبيل: (+2) 01001050113 -01227348893- 01003405080



Website: www.alphastone-eg.com

Email: alphastone.factory@yahoo.com