




**ALPHA STONE**

for grinding & packing  
calcium carbonate

## PRODUCTS:

### PLASTIC KAOLINE (CHEMICAL ANALYSIS)

PLASTIC CAOLIN	ELEMENT	RESULT %
	Al <sub>2</sub> O <sub>3</sub>	32.00 - 38.00
	Fe <sub>2</sub> O <sub>3</sub>	0.20 - 0.70
	SiO <sub>2</sub>	45.00 - 50.00
	CaO	0 - 0.50
	K <sub>2</sub> O	0 - 0.10
	Na <sub>2</sub> O	0 - 0.05
	TiO <sub>2</sub>	1.00 - 2.00
	Cl	0 - 0.50
	Mn <sub>2</sub> O <sub>3</sub>	0 - 0.20
	MgO	0 - 0.30
	P <sub>2</sub> O <sub>5</sub>	0 - 0.10
	O.M.	6.00 - 7.00
	L.O.I	11.00 - 13.00

#### USERS:

- CERAMICS
- RUBBER
- PAPER
- PAINTS